

Scan this QR code with your smartphone for:

- Product Data Sheet and SDS
- Non-English Product Information
- Additional Product Information



Fiberlock

TECHNOLOGIES

Professional Products
Professional Results

CAUTION!
KEEP OUT OF REACH OF CHILDREN.
Do not take internally. Close container after each use.
Keep from freezing.
Store between 40°F (4.5°C) and 90°F (32°C)
24 hour Emergency "CHEM-TEL" - 1-800-255-3924

CAS. No.:
7732-18-5
13463-67-7
1314-13-2
1317-65-3
1332-58-7
Not Available*
*Contents partially unknown

CHEMICAL INGREDIENTS:
Water
Titanium dioxide
Zinc oxide
Calcium Carbonate
Aluminum Silicate
Latex resin solids

WARNING: This product contains chemicals known to the State of California to cause cancer, birth defects, or other reproductive harm.

Calculated VOC: 93 g/l

WARNING:



Hazard Statements:
Harmful if inhaled.
Causes serious eye irritation.
May cause an allergic skin reaction.
May cause cancer.

Precautionary Statements:

Prevention: Obtain special instructions before use. Do not handle until all safety precautions have been read and understood. Use personal protection (eye protection, gloves) during application. When grinding/sanding dry films, wear respiratory protection.

Response: If on skin, wash with plenty of soap and water. If in eyes, rinse cautiously for several minutes. Remove contact lenses if present and easy to do. Continue rinsing. If inhaled, remove victim to fresh air. If exposed or concerned, get medical advice.

Storage: Keep closures tight and containers upright to prevent leakage. KEEP FROM FREEZING. Product is non-combustible.

Disposal: The coating and any contaminated diking material should be thoroughly air dried and collected into drums. The drums should be sealed and labeled and land-filled or incinerated according to local, regional and national regulations.

Emergency Tel. No.: CHEM TEL: (U.S.): 1-800-255-3924
(Outside the U.S.): 813-248-0585

For Technical Information call 800.342.3755

These suggestions and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee, as conditions and methods of use of this product are beyond our control. Neither ICP Construction, Inc., nor its agents shall be responsible for the use of this product or any procedures or apparatus mentioned. We recommend that the prospective user determine the suitability of IAQ 5000, for each specific project and for the health and safety of personnel working in the area.

For additional information check Safety Data Sheet (SDS) or Product Data Sheet (PDS) available online at www.fiberlock.com.

IAQ, the IAQ Logo and other marks on this label are trademarks of ICP Construction, Inc.

8350-5 White



150 Dascomb Rd.
Andover, MA 01810
(800) 342-3755
www.fiberlock.com

IAQ

5000

Stain Blocking Primer

- Superior stain blocking
- Excellent adhesion to glossy surfaces

*Resists mold growth on the dry coating surface.

NET CONTENTS: 5 Gallons

For Professional Use Only

IAQ 5000 is a white, quick drying, high performance 100% acrylic latex coating specifically designed to prime stained or water damaged surfaces. IAQ 5000 provides exceptional adhesion and stain blocking properties and may be used on interior or exterior surfaces to prevent most bleeding type stains, seal porous surfaces and provide adhesion to hard and glossy surfaces. IAQ 5000 also contains a fungistatic agent to resist mold growth on the dry coating surface. IAQ 5000 provides maximum breathability, adhesion, and holdout to prolong the life of the finish. IAQ 5000 is recommended for use on wallboard, plaster, sheetrock, masonry, wood, concrete, aluminum, and galvanized metal.

PRODUCT APPLICATION

Material is supplied at application consistency but can be thinned sparingly with water if necessary to improve application characteristics. Thin with no more than 8oz. of water per gallon. Apply with appropriate application equipment. Some stains may require two coats of IAQ 5000; if an active stain discolors the primer, apply an additional coat to a small area to see if the stain is "locked" into the primer.

COVERAGE

Smooth Surfaces: 400-500 ft²/gal.
Porous Surfaces: 100-300 ft²/gal.

DRYING TIME @ 70°F 50% R.H

To Touch: 30 minutes
Recoat: 2 hours

CLEANUP

Clean tools and drippings with warm soapy water before IAQ 5000 dries. Dispose of waste according to all existing local, state and federal regulations.

PRECAUTIONS

Store in a dry place at temperatures between 40°F (4.5°C) and 90°F. (32°C). Stir thoroughly. Do not mix with any other coatings, solvents or colors in oil. The IAQ 5000 coating is resistant to mold only on the surface of the coating. No mold resistance claim is made other than to the coating itself. Do not apply when air or surface temperature is below 50°F, or when drying conditions are poor or when surfaces are above a 15% moisture level content. Use adequate ventilation during application. When applying with a sprayer, wear a NIOSH approved respirator with any R, P, N or HE filter. For interior use only.

SURFACE PREPARATION

Warning! If you scrape, sand, or remove old paint from any surface, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Carefully clean up with a wet mop and HEPA vacuum. Before you start, find out how to protect yourself and your family by contacting the U.S. EPA/Lead Information Hotline at 1-800-424-LEAD(5323) or log on to www.epa.gov/lead.

Surfaces to be coated must be free of dust, mildew, mold, dirt, grease, loose paint, oil, glue size, calcimine, wax, soap and other surface contamination. Clean mold stained surfaces with IAQ Advanced Peroxide Cleaner, or use an EPA registered antimicrobial disinfectant cleaner such as IAQ 2000, IAQ 2500, ShockWave or ShockWave RTU.

Fill nicks, holes and voids with appropriate patching material and sand smooth prior to priming.

APPLICATION TOOLS

Apply IAQ 5000 with brush, roller or airless spray equipment.

Brush: Synthetic, nylon or polyester bristle
Roller: Synthetic fiber 3/8" nap or longer
Spray: .015 to .023 tip @ 2200-2800 P.S.I.