



74 Kent Street
Brooklyn, New York 11222-1517

Phone (718) 383-5080
Fax (718) 383-7445
E-mail: dlabs@aol.com

Accredited by National Voluntary Laboratory Accreditation Program - Lab Code 100252
Accepted by Canadian General Standards Board - No. 76005 - ISO/IEC 25 Approved

July 12, 2002

Fiberlock Technologies, Inc
150 Dascomb Road
Andover MA 01810-5873

Att: Mr. Andre Weker

Re: DL-13527
Via FAX (978)-475-6205

OBJECTIVE

To evaluate the resistance of a coating to mold and fungal growth.

PRODUCT TESTED

The coating was submitted by Fiberlock Technologies, Inc. for testing and identified as IAQ 6100, Lab 121-73.

PROCEDURE

The resistance to mold and fungal growth of the coating was evaluated in accordance with procedures outline in ASTM G 21, "Standard Practice for Determining Resistance of Synthetic Polymeric Materials to Fungi".

The coating was cast to produce a free film and allowed to cure a minimum of seven days at standard conditions before testing was initiated. Replicate specimens, measuring 1 X 1-inch were exposed to a mixed fungal spore suspension consisting of *Aspergillus niger*, *Aureobasidium pullulans*, *Chaetomium globosum*, *Gliocladium virens* and *Penicillium pinophilum*.

TEST RESULTS

The submitted coating, namely IAQ 6100, Lab 121-73, exhibited a 0-rating for fungal resistance; indicating no fungal growth on the surface area of the specimens. The specimens did not exhibit a zone of inhibition.

DL Labs, Inc.

A handwritten signature in black ink, appearing to read 'Mario Lazaño, Jr.'.

Mario Lazaño, Jr.
Assistant Technical Director

cc: T. J. Sliva

This report may contain test data obtained from test methods not covered by NVLAP accreditation. See reverse side for those test methods which are covered.

This report shall not be reproduced except in full without the prior written approval of the DL Labs, Inc. The information contained herein is not endorsed by NVLAP, CGSB or any agency of the U.S. or Canadian governments and no such endorsement may be claimed.