

March 13, 1992

Fiberlock Technologies 630 Putnam Ave. cambridge, MA. 02139-0432 Attn. Mark

## Dear Mark:

We have tested our adhesives for compatibility with your Fiberset FT and Fiberlock ABC. The tests were performed to see if the adhesives were compatible with your sealers and if any reactions occurred.

The test results showed that there were no loss of bond strength when materials were adhered over your two sealers at the thickness recommended by Fiberlock Technologies.

The adhesives tested were 137 Acoustical Tile Adhesive, 237 Latex based Acoustical Tile Adhesive, 251 "The Sticker" Carpet Adhesive, and 356 Multi-Purpose White Latex Adhesive. Other flooring adhesives in our line were not tested but they are similar in nature to 356.

It is not our policy to recommend the Acoustical Tile Adhesive over anything but a clean substrate. This is due to the liability involved. If you would like to discuss the above please call me at 1 (800) 232-4832.

Whent

Wally Giambastiani Product Development Manager

cc: M. Glennon

CORPORATE OFFICE: 5608 Soto St., Huntington Park, CA 90255 • (213) 583-4961 • FAX (213) 582-8451 MANUFACTURING PLANTS:

5920 Alamo Street, Maywood, CA 90270 • (213) 583-4961 • FAX (213) 771-6188 210 W. Taft Avenue, Orange, CA 92667 • (714) 282-1240 • FAX (714) 974-6133 350 S. Industrial Park Drive • P.O. Box 829 • Dallas, GA 30132 • (404) 445-5377 3233 W. 36th Street, Chicago, IL 60632 • (312) 254-3510 • FAX (312) 254-7624 Foot of Whitehead Avenue, South River, NJ 08882 • (201) 254-2424 • FAX (201) 254-8683 520 W. 3rd Street, Dover, OH 44622 • (216) 343-4535 • FAX (216) 343-6387 1101 Avenue G East, Arlington, TX 76011 • (817) 649-8070 • FAX (817) 633-4408