


BS 6853:1999: Annex B.2



Determination of weighted summation of toxic fume, R – Area based test method

A Report To: Fiberlock Technologies Inc.

Document Reference: 338606

Date: 13th June 2014

Issue No.: 1

Page 1

Testing
Advising
Assuring

Executive Summary

Objective To determine the toxic fume produced from the following product when tested in accordance with BS 6853: 1999 incorporating amendment No. 1: Annex B.2:



Generic Description	Product reference	Thickness	Weight per unit area or density
A water-based coating product applied to a calcium silicate substrate	"SerpiMastic Sprayable - Part #2419"	13.2mm *	12.7kg/m ² *
Individual components used to manufacture composite:			
Coating product (test face)	"Part #2419"	1mm	Not stated
Calcium silicate	"Promat-Brandschutzbauplatten; Promatect-H"	12mm	870kg/m ³
*Determined by Exova Warringtonfire			
Please see page 5 of this test report for the full description of the product tested			

Test Sponsor Fiberlock Technologies Inc., 150 Dascomb Road, Andover, Massachusetts 01810, USA.

Summary of Test Results: The R Value determined was **0.30**.

Date of Test 3rd June 2014

Signatories

	
Responsible Officer C. Lester * Technical Officer	Authorised S. Deeming * Operations Manager

* For and on behalf of **Exova Warringtonfire**.

Report Issued: 13th June 2014

This version of the report has been produced from a .pdf format electronic file that has been provided by **Exova Warringtonfire** to the sponsor of the report and must only be reproduced in full. Extracts or abridgements of reports must not be published without permission of **Exova Warringtonfire**.

CONTENTS	PAGE NO.
EXECUTIVE SUMMARY	2
SIGNATORIES	2
TEST DETAILS	4
DESCRIPTION OF TEST SPECIMENS	5
TEST PROCEDURE.....	6
TEST RESULTS.....	7
TABLE 1.....	9
REVISION HISTORY.....	10



Test Details

Introduction

Exova Warringtonfire was commissioned to carry out an area based toxicity test in accordance with the method recommended in BS 6853:1999 Incorporating Amendment 1, Informative Annex B.2. This standard recommends that the test is carried out using the apparatus detailed in prEN2824 but the ignition cone used should conform with the requirements given in BS ISO 5659-2 and that the quantitative determination of the gases emitted should be carried out in accordance with the procedure specified in prEN2826.

The test was performed in accordance with the procedure specified in prEN2825 and prEN2826 amended in accordance with the recommendations given in BS6853: 1999 Annex B and this report should be read in conjunction with these and other related standards.

Test method

The principle of the test methods detailed in prEN2825 and prEN2826 is to expose a material to specified thermal conditions of pyrolysis and combustion in a continuous procedure. The change in optical density of the smoke produced when dispersed within a fixed volume of air is recorded throughout the period of test. Quantitative determination of toxic gases emitted is carried out using wet analysis.

The test method provides a means for the comparative assessment of products, however, it does not model a real fire situation and the results cannot therefore be used to describe the fire hazard of materials under actual fire conditions.

Fire test study group/EGOLF

Certain aspects of some fire test specifications are open to different interpretations. The Fire Test Study Group and EGOLF have identified a number of such areas and has agreed Resolutions which define common agreement of interpretations between fire test laboratories which are members of the Groups. Where such Resolutions are applicable to this test they have been followed.

Instruction to test

The test was conducted on the 3rd June 2014 at the request of Fiberlock Technologies Inc., the sponsor of the test.

Provision of test specimens

The coating system was supplied by the sponsor of the test. **Exova Warringtonfire** supplied the substrate and a third party contractor applied the coating system to the substrate. **Exova Warringtonfire** was not involved in any selection or sampling procedure.

Conditioning of specimens

The specimens were received on the 12th May 2014.

Prior to the tests, the coatings were applied and allowed to cure for a period of 14 days prior to all of the specimens being conditioned to constant mass at a temperature of $23 \pm 2^\circ\text{C}$ and a relative humidity of $50 \pm 5\%$. One specimen from the total sample submitted for test was selected for constant mass verification.

Test Face

The coated face of the specimen was exposed to the radiant heat source.

Description of Test Specimens

The description of the specimens given below has been prepared from information provided by the sponsor of the test. All values quoted are nominal, unless tolerances are given.

General description		A water-based coating product applied to a calcium silicate substrate
Thickness of composite including substrate		13.2mm (determined by Exova Warringtonfire)
Weight per unit area of composite including substrate		12.7kg/m ² (determined by Exova Warringtonfire)
Product reference of overall coating		"SerpiMastic Sprayable - Part #2419"
Coating product (test face)	Generic type	Water-based, high solids, asbestos bridging encapsulant/mastic coating
	Product reference	"Part #2419"
	Name of manufacturer	Fiberlock Technologies, Inc.
	Colour reference	"Off White"
	Number of coats	1
	Application thickness per coat	1 mm
	Application rate per coat	0.4m ² /l
	Application method	Airless spray
	Flame retardant details	See Note 1 below
Curing process per coat		14 days minimum
Calcium silicate	Trade name	"Promat-Brandschutzbauplatten; Promatect-H"
	Generic type	Calcium silicate based board
	Name of manufacturer	Promat
	Thickness	12mm
	Density	870kg/m ³
Flame retardant details		This component is inherently flame retardant
Brief description of manufacturing process		Dispersion and mixing of resins, pigments, and additives to form a water based coating

Note 1: The sponsor was unwilling to provide this information.

Test Procedure

Specimens were tested in the flaming mode in a horizontal position by exposure to the heating arrangement specified in ISO 5659-2. The heat flux was 25kW/m².

The sampling and analysis of the fire gases generated during the test is conducted using a variety of methods as defined in the internal operating procedure.

In all cases, the sample is taken from the geometric centre of the chamber with sample lines being kept as short as possible to minimise sample losses.

For the analysis of oxides of carbon and nitrogen, continuous measurements are made throughout the duration of the test.

Carbon dioxide (CO₂) and carbon monoxide (CO) are determined continuously using precalibrated non-dispersive infra-red analysers. The values reported are those measured at 85% smoke obscuration.

Oxides of nitrogen (NO_x) are determined continuously using a chemiluminescence analyser. Again, the values reported are those measured at 85% smoke obscuration.

For the other gases, single point analysis is conducted, the gases being absorbed into an aqueous media and analysed remotely. Two types of media are used, 0.1M sodium hydroxide solution and 0.3% hydrogen peroxide solution. The gases are sampled over a two minute period commencing when smoke density has reached 85% obscuration by bubbling the gases through the aqueous media using a fitted funnel Dreschel bottle arrangement.

Hydrogen cyanide (HCN) is determined from gases absorbed into a 0.1M solution of sodium hydroxide and analysed using ion chromatography. The concentration determined is an average over each 2 minute period beginning at 85% smoke obscuration.

Hydrogen chloride (HCl), hydrogen bromide (HBr), hydrogen fluoride (HF) and sulphur dioxide (SO₂) are absorbed into a 0.3% solution of hydrogen peroxide and are also analysed by ion chromatography. The concentration determined is an average over each 2 minute period beginning at 85% smoke obscuration.

Test Results

Applicability of test results

The test results relate only to the behaviour of the specimens of the product under the particular conditions of test; they are not intended to be the sole criterion for assessing the potential smoke and toxicity hazard of the product in use.

The test results relate only to the specimens of the product in the form in which they were tested. Small differences in the composition or thickness of the product may significantly affect the performance during the test and will therefore invalidate the test results. It is the responsibility of the supplier of the product to ensure that the product which is supplied is identical with the specimens which were tested.

Gases sampled

One specimen was tested to determine the Ds_{max} and time to Ds_{max} . From the results of this test time to reach 85% of Ds_{max} was calculated. The results are given below:

Ds_{max}	19
Time to Ds_{max} (T_{max})	11:00
Time to 85% of Ds_{max} (T_{max} 85%)	8:00

Three further specimens were then tested. Gases generated were sampled after eight minutes test duration. The quantitative determinations were then carried out using the procedures described. The test results obtained are provided below and test observations are detailed in Table 1.

Gas	Specimen No. 1	Specimen No. 2	Specimen No. 3	Average
Carbon Monoxide	8.85	10.86	16.79	12.16
Carbon Dioxide	917.07	902.38	637.97	819.14
Sulphur Dioxide	ND	ND	ND	ND
Hydrogen Chloride	ND	ND	ND	ND
Hydrogen Bromide	ND	ND	ND	ND
Hydrogen Fluoride	ND	ND	ND	ND
Hydrogen Cyanide	ND	ND	ND	ND
Nitrogen Oxides	1.82	1.82	0.83	1.49

Where: ND indicates non-detected.
 Note: All values given are in g/m^2 .

Weighted Summation of Toxic Fume, R

The test results obtained for toxicity measurements were used to calculate the weighted summation index, R, as described in BS 6853: 1999: Annex B.4.2.

The R Value determined was 0.30.

Validity

The specification and interpretation of fire test methods are the subject of ongoing development and refinement. Changes in associated legislation may also occur. For these reasons it is recommended that the relevance of test reports over five years old should be considered by the user. The laboratory that issued the report will be able to offer, on behalf of the legal owner, a review of the procedures adopted for a particular test to ensure that they are consistent with current practices, and if required may endorse the test report.

This report may only be reproduced in full. Extracts or abridgements shall not be published without permission of **Exova Warringtonfire**

Table 1

Testing with Flame Application									
Specimen	D _s after t in minutes							D _s max. within 1.5 min	D _s max. within 4 min
	1	1.5	2	3	4	5	6		
Smoke run	1	1	1	2	3	5	9	1	3

Observations during test

Specimen No.	Initial Smoke Production Test	Toxicity Tests		
		1	2	3
Colour of smoke produced	Dark	Dark	Dark	Dark
Expansion distance towards heater (mm)	N/A	N/A	N/A	N/A
Ignition time in seconds (if applicable)	114	74	112	80
Extinction time in seconds (if applicable)	240	235	227	254
Re-ignition time in seconds (if applicable)	*	*	*	*
Extinction time in seconds (if applicable)	N/A	N/A	N/A	N/A
* = Did Not Re-ignite N/A = Not Applicable				

Revision History

Issue No :	Issue Date:
Revised By:	Approved By:
Reason for Revision:	

Issue No :	Issue Date:
Revised By:	Approved By:
Reason for Revision:	